

Polystal® - GRP P160

High-performance composite profiles

Polystal® GRP is a composite of glassfibres and synthetic resin. The distinctive Polystal® surface is sealed with resin and lubricant free owing to the state-of-the-art manufacturing procedure. The material can thus be easily up-jacketed with thermoplastics and offers the most excellent processing performance.

PHYSICAL PROPERTIES

Glass Content	(%)	80 ± 2.5 %	(DIN EN ISO 1172)
Density	(g/cm ³)	2.1	(DIN 53479)
Modulus of elasticity	(N/mm ²)	> 50,000	(DIN EN ISO 527-4)
Tensile strength of area	(N/mm ²)	1,500 ± 5 %	(DIN EN ISO 527-4)
Elongation at break	(%)	> 2.5	(DIN EN ISO 527-4)
Ovality	(%)	< 6	
Coefficient of Thermal Expansion (CTE)	(1/°C)	6.6 x 10 ⁻⁶	(DIN ISO 7991)
Absorption of Water	(%)	≤ 0.1	(DIN EN ISO 62)
Electrical Resistance	(Ω cm)	1.6 x 10 ¹⁶	(ASTM D 257)
Electrical Surface Resistance	(Ω)	1.3 x 10 ¹⁴	(ASTM D 257)
Dielectric Coefficient at 1 MHz	(E _r)	4.9	(ASTM D 150)
Loss Factor at 1 MHz	(tan δ)	0.0093	(ASTM D 150)

CHARACTERISTIC VALUES

Outside Diameter (tolerance)	(mm) (inches)	16.00 (± 0.20) 0.62992 (± 0.00787)	
Performance Diameter	(mm) (inches)	16.00 0.62992	
Weight	(g/m)	420.00 ± 4 %	
Force at Break	(N)	301,440* ± 5 %	(DIN EN ISO 527-4)
Tensile Force at 0.5 % Elongation at 1.0 % Elongation	(N) (N)	47,040 94,080*	(DIN EN ISO 527-4)
Minimum Bend Diameter at 25 °C	(mm) (inches)	1,600.0 62.99200	
Longtime Flexion Test at 1 % RFD and 80 °C after 24 h at 2 % RFD and 25 °C after 24 h		without break or delamination without break or delamination	Siemens-Method

RFD Strain of the egde fibers

*calculated values

Polystal® is a registered Trademark. Data provided in this document is for information purposes only. Polystal Composites GmbH reserves the right to improve, enhance and modify the features and specifications of Polystal products without prior notice. Polystal Composites GmbH thus makes no warranty, express or implied, that the current product conforms to these specifications. Please contact Polystal Composites GmbH or an authorized representative to make sure that current products will match your specific requirements.

Polystal Composites GmbH warrants that its products will work in a manner consistent with the capabilities for which they were designed. This warranty shall be void if the product has been manipulated or used improperly.

Except for the express warranty and limited remedies described above. Polystal Composites GmbH disclaims all other warranties including implied warranties. Polystal Composites GmbH and its authorized representatives shall have no other liability beyond the price of the product for damage to a purchaser, including consequential damages, occurring in connection with the use or performance of the product.

If sections or individual terms of this statement are not legal or correct, the content or validity of the other parts remain uninfluenced by this fact.

